

FinLight®

TECHNICAL DATA

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm				
			35	38	40	50	60
Mdf Faces Thicknesses		mm	3	3	3	3	6
Density (*)	EN 323:1993	kg/m³	410-380	410-380	410-380	380-360	390
Internal Bond	EN 319:1993	N/mm²	0,06	0,06	0,06	0,06	0,06
Thickness Swelling 24h	EN 317:1993	%	10	10	10	9	7
Bending Strength	EN 310:1993	N/mm²	5	5	5	5	5
Modulus of Elasticity	EN 310:1993	N/mm²	1300	1300	1300	1200	1200
Surface Soundness	EN 311:2002	N/mm²	1,2	1,2	1,2	1,2	1,2
Dimensional Movement Length/Width	EN 318:2002	%	0,30	0,30	0,30	0,30	0,30
Dimensional Movement Thickness	EN 318:2002	%	3	3	3	3	3
Screw Holding. Surface	EN 320:2011	N	600	600	600	600	600
Grit Content	ISO 3340:1976	% Weight	≤ 0,05	≤ 0,05	≤ 0,05	≤ 0,05	≤ 0,05
Moisture Content	EN 322:1993	%	7+/-3	7+/-3	7+/-3	7+/-3	7+/-3

TOLERANCE ON NOMINAL DIMENSIONS

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm				
			35	38	40	50	60
Thicknesses	EN 324-1:1993	mm	+/-0,30	+/-0,30	+/-0,30	+/-0,30	+/-0,30
Lenght & Width	EN 324-1:1993	mm	+/- 3 mm/m	+/- 3 mm/m	+/- 3 mm/m	+/- 3 mm/m	+/- 3 mm/m
Squareness	EN 324-2:1993	mm/m	+/- 3	+/- 3	+/- 3	+/- 3	+/- 3

(*) Values to be considered as a rough guide only.

Reports and certificates relating to this product are available upon request.

Handling/Storage Recommendations:

Boards should always be stored under cover and on a flat surface.
Optimal storage conditions are 65% humidity; avoid environments that are either too dry or too damp.
Under no circumstances should there be direct contact with water.
Spacers must always be vertically aligned.
Under no circumstances should boards be stacked more than 4 high.

If the packaging is damaged during handling, it must be re-packaged to ensure the product's proper preservation.

Failure to observe the stated stacking conditions, as well as changes in humidity or temperature in warehouses or processing areas, can lead to irreversible distortion and warping.

Wood used by Finsa in the production of fibreboards (MDF) is a mixture primarily of pine and eucalyptus. Particleboard production also uses a mixture primarily of pine and eucalyptus, with the addition of recycled wood from diverse species. All wood is obtained in accordance with PEFC and FSC chain of custody requirements, and in compliance with EUTR/EUDR regulations.

It is the duty and responsibility of the end user to evaluate, in accordance with relevant local health and safety regulations, all risks presented to any persons involved in processing/transforming/handling the materials. A detailed plan of procedure and necessary checks must be in place to ensure preventive measures are appropriately enforced to minimise all risk; eg. manual handling, dust extraction if cutting/sanding/machining, use of PPE, etc.