

SuperPan® Tech Encoform P5 EZ Gris

TECHNICAL DATA

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm	
			13-20	>20-25
Density (*)	EN 323:1993	kg/m ³	700/690	690/680
Formaldehyde emission	EN 717-1:2004	ppm	≤ 0.05	≤ 0.05
Thickness Swelling 24h	EN 317:1993	%	10	10
Moisture Content	EN 322:1993	%	8+/-3	8+/-3
Modulus of Elasticity	EN 310:1993	N/mm ²	3500	3500
Bending Strength	EN 310:1993	N/mm ²	28	26
Swelling In Thickness after Cyclic Test (V313)	EN 321:2001 / EN 317:1993	%	12	11
Internal Bond after Cyclic Test (V313)	EN 321:2001 / EN 319:1993	N/mm ²	0,22	0,20
Internal Bond	EN 319:1993	N/mm ²	0,65	0,65
Surface Soundness	EN 311:2002	N/mm ²	1,1	1,1
Reaction to fire	EN 13501-1:2018	Euroclass	CWFT	CWFT

TOLERANCE ON NOMINAL DIMENSIONS

PROPERTIES	TEST METHOD	UNITS	THICKNESSES mm	
			13-20	>20-25
Squareness	EN 324-2:1993	mm/m	+/- 2	+/- 2
Thicknesses	EN 324-1:1993	mm	+/- 0,3	+/- 0,3
Lenght & Width	EN 324-1:1993	mm	+/- 5	+/- 5
Edge Straightness	EN 324-2:1993	mm/m	+/- 1,5	+/- 1,5

COATING PROPERTIES

PROPERTIES	TEST METHOD	UNITS	SPECIFICATION
Resistance to Cracking	EN 14323:2021	Rating	≥ 3
Resistance to Staining	EN 14323:2021	Rating	≥ 3
Resistance to Scratching	EN 14323:2021	N	≥ 1.5

RESISTANCE TO ABRASION

PROPERTIES	TEST METHOD	CLASS	IP NUMBER OF TURNS
Abrasion resistance. Unicolors and AH Products	EN 14323:2021	3A	≥ 150
Abrasion resistance	EN 13329:2023	Class	≥ 500 (AC1)

(*) Values to be considered as a rough guide only.

These physical-mechanical values comply with the values established in European standard EN 312:2010, Tables 7 and 8. - Structural boards for use in humid conditions (Type P5).

CWFT: Reaction to fire classification without the need of testing, according to European Commission Decision 2007/348/EC.

Product with very low formaldehyde emission ≤ 0.05 ppm (≤ 0.062 mg/m³) measured under European Standard EN 717-1:2004 that complies with the specifications of Class E1 defined in th EN 312:2010 European Standard.

Product compliant with US EPA TSCA Title VI and California Code of Regulation 17 ATCM 93120, Phase 2.

Product tested by IMSL under the Standard ISO 22196:2011, verifying that inhibits the growth and development of bacteria without affecting the characteristics of the coating.

SuperPan Tech Encoform P5 EZ Gris is supplied with sealed and protected edges (grey colour)

Reports and certificates relating to this product are available upon request.



SuperPan® Tech Encoform P5 EZ Gris

Handling/Storage Recommendations:

Boards should always be stored under cover and on a flat surface.

Optimal storage conditions are 65% humidity; avoid environments that are either too dry or too damp.

Under no circumstances should there be direct contact with water.

Spacers must always be vertically aligned.

Under no circumstances should boards be stacked more than 4 high.

If the packaging is damaged during handling, it must be re-packaged to ensure the product's proper preservation.

Failure to observe the stated stacking conditions, as well as changes in humidity or temperature in warehouses or processing areas, can lead to irreversible distortion and warping.

Wood used by Finsa in the production of fibreboards (MDF) is a mixture primarily of pine and eucalyptus. Particleboard production also uses a mixture primarily of pine and eucalyptus, with the addition of recycled wood from diverse species. All wood is obtained in accordance with PEFC and FSC chain of custody requirements, and in compliance with EUTR/EUDR regulations.

It is the duty and responsibility of the end user to evaluate, in accordance with relevant local health and safety regulations, all risks presented to any persons involved in processing/transforming/handling the materials. A detailed plan of procedure and necessary checks must be in place to ensure preventive measures are appropriately enforced to minimise all risk; eg. manual handling, dust extraction if cutting/sanding/machining, use of PPE, etc.